

## DATA SHEET

**BX-2000**

PRODUCT DESCRIPTION : Biaxial geogrid, extruded in a single layer

FUNCTION : Reinforcement

RAW MATERIAL : Polypropylene

### TECHNICAL DATA TABLE

	PROPERTIES	TEST METHOD	VALUES	
			Metric	Imperial
PHYSICAL	Aperture size	-	39 mm x 39 mm (± 1 mm)	1.54 in x 1.54 in (± 0.04 in)
	Carbon black content	ASTM D4218	2%	
	Average rib thickness	-	1.3 mm	52 mils
MECHANICAL	Tensile strength. at 2 % strain <sup>(1)</sup>	ASTM D6637	8 kN/m	548 lb/ft
	Tensile strength. at 5 % strain <sup>(1)</sup>	ASTM D6637	14 kN/m	959 lb/ft
	Ultimate tensile strength <sup>(1)</sup>	ASTM D6637	19 kN/m	1302 lb/ft
	Junction strength <sup>(1)</sup>	GRI-GG2	19 kN/m	1302 lb/ft
	Flexural stiffness/rigidity	ASTM D7748	1585 g-cm (MD) - 930 g-cm (CMD)	
	Aperture stability <sup>(2)</sup>	-	3.4 kg-cm/deg @ 20 kg-cm torque	
	Radial stiffness at low strain <sup>(3)</sup>	-	284.9 kN/m @ 0.5 % strain	
	Multi-axial tension test	-	-	
	- Vessel pressure at rupture	-	73 kPa	10.6 psi
	- Axisymmetric break resistance strain	ASTM D7748	8.3 %	
- Average deflection at rupture	-	109 mm	4360 mils	
PERFORMANCE AND DURABILITY	pH resistance	-	2 - 13	
	UV** resistance (500 hours)	ASTM D4355	100%	
DIMENSIONS	Standard width	-	3.95 m	13 ft
	Standard length	-	50 m	164 ft

NOTE 1 : Values shown are MARV as per GRI.

NOTE 2 : In-plane torsional rigidity, measured by applying a moment of 20 kg-cm, at the central junction of a 225 mm x 225 mm specimen (8.85 in x 8.85 in).

*U.S. Army Corps of Engineers Methodology (Kinney, T.C. Aperture Stability Modulus ref 3, 3.1.2000).*

NOTE 3 : Radial stiffness is determined from tensile stiffness measured in any in-plane axis from testing in accordance with ASTM D6637-01.

The information contained herein is provided at no cost or obligation on the part of Soleno Textile Inc. The individual using this information in their possession assumes full responsibility for its use, including that of ensuring that this technical data sheet is the latest update by contacting Soleno Textile Inc. Values are calculated using the minimum average roll value (MARV), as defined by ASTM D-4439. Roll sizes can vary 0.5% from standard sizes.

Soleno Textile Inc. offers no guarantee regarding the use, installation or fitness for purpose of its geotextiles described in this document. Since conditions of use and handling of our products can vary and are beyond the control of Soleno Textile Inc., it can in no way be held responsible for the product's performance and the consequences of improper installation or use. Soleno Textile Inc. must be advised of any defect or non-compliance of its product before installation. Soleno Textile Inc.'s liability is limited to the replacement of the defective or noncompliant product, with the exception of any legal or contractual warranty.

APPLICATIONS :

Temporary roadway	Storage and loading areas
Permanent public roadway	Roadway widening
Permanent private roadway	Airport runways
Public access road	Railway track
Commercial parking areas	