

DATA SHEET

TX-F

PRODUCT DESCRIPTION : Nonwoven needled geotextile mainly used in forestry

FUNCTIONS : Reinforcement

RAW MATERIAL : Polypropylene

TECHNICAL DATA TABLE

	PROPERTIES	TEST METHOD	VALUES	
			Metric	Imperial
PHYSICAL	Thickness	ASTM D5199	1,5 mm	60 mils
	Tensile strength	CAN/CGSB-148,1 - No 7,3	1000 N	225 lb
MECHANICAL	Elongation at break	CAN/CGSB-148,1 - No 7,3	50 - 100 %	
	Tear strength	CAN/CGSB-4,2 - No 12,2	350 N	79 lb
	Puncture strength (CBR)	ASTM D6241	2800 N	629 lb
HYDRAULIC	Permeability	CAN/CGSB-148,1 - No 4	0,22 cm/s	
	Filtration opening size (FOS)	CAN/CGSB-148,1 - No 10	50 - 80 µm	
PERFORMANCE AND DURABILITY	UV* resistance (500 hours)	ASTM D4355	50 %	
DIMENSIONS	Standard width	-	3,5 m	11,5 ft
	Standard length	-	100 m	328 ft

*UV: Ultraviolet.

The information contained herein is provided at no cost or obligation on the part of Soleno Textile Inc. The individual using this information in their possession assumes full responsibility for its use, including that of ensuring that this technical data sheet is the latest update by contacting Soleno Textile Inc. Values are calculated using the minimum average roll value (MARV), as defined by ASTM D-4439. Roll sizes can vary 0.5% from standard sizes

Soleno Textile Inc. offers no guarantee regarding the use, installation or fitness for purpose of its geotextiles described in this document. Since conditions of use and handling of our products can vary and are beyond the control of Soleno Textile Inc., it can in no way be held responsible for the product's performance and the consequences of improper installation or use. Soleno Textile Inc. must be advised of any defect or non-compliance of its product before installation. Soleno Textile Inc.'s liability is limited to the replacement of the defective or noncompliant product, with the exception of any legal or contractual warranty.

APPLICATIONS : Temporary roadway

