

## **DATA SHEET**

## ROUTEX II

PRODUCT DESCRIPTION: Geocomposite combining a nonwoven needled geotextile reinforced with a woven geotextile

## MAIN FUNCTION: Reinforcement

PRODUCT CERTIFICATION: Standard BNQ 7009-210/2017, using protocol BNQ 7009-910/2018 and the grade R1 Compliant with the CCDG of MTQ

RAW MATERIAL: Polypropylene

## **TECHNICAL DATA TABLE**

	PROPERTIES	TEST METHOD	VALUES	
			Metric	Imperial
PHYSICAL	Thickness <sup>(1)</sup>	ASTM D5199	≥ 0.8 mm	≥ 32 mils
	Mass per unit area (1)	ASTM D5261	-	-
MECHANICAL	Wide width tensile strength, at break, at < 5 $\%$ of CVMS*	ASTM D4595	$\geq$ 13.0 kN/m	$\geq$ 74.1 lb/in
	Wide width tensile strength, at break, at 5 $\%$ to < 10 $\%$ of CVMS*	ASTM D4595	≥ 13.65 kN/m	≥ 77.8 lb/in
	Wide width tensile strength, at break, at 10 $\%$ to < 15 $\%$ of CVMS*	ASTM D4595	$\geq$ 14.3 kN/m	$\geq$ 81.5 lb/in
	Wide width tensile strength, at 5 % elongation, at < 5 % of CVMS*	ASTM D4595	$\geq$ 5.0 kN/m	≥ 28.5 lb/in
	Wide width tensile strength, at 5 $\%$ elongation, at 5 $\%$ to < 10 $\%$ of CVMS*	ASTM D4595	≥ 5.78 kN/m	≥ 32.9 lb/in
	Wide width tensile strength, at 5 $\%$ elongation, at 10 $\%$ to < 15 $\%$ of CVMS*	ASTM D4595	$\geq 6.05 \text{ kN/m}$	≥ 34.5 lb/in
	Elongation at break	ASTM D4632	< 30	
	CBR Puncture resistance	ASTM D6241	≥ 2300 N	≥ 517 lb
HYDRAULIC	Permeability (1)	ASTM D4491	$\geq$ 0.01 cm/s	
	Permittivity	ASTM D4491	$\geq 0.05 \text{ s}^{-1}$	
	Filtration opening size (FOS)	CAN/CGSB-148.1 - No 10-94	45 - 150 μm	
	Transmissivity	ASTM D6574	$\ge 10^{-7}  m^2/s$	
PERFORMANCE AND DURABILITY	UV** resistance (500 hours)	ASTM D4355	≥ 70 %	
DIMENSIONS	Standard width <sup>(1)</sup>	-	3.5 m	11.5 ft
	Standard length (1)	-	100.0 m	328.0 ft

Note 1: Property not part of the product certification by the BNQ.

\*CVMS : Coefficient of variation of Mass per unit area. \*\* UV: Ultraviolet.

The enclosed information is provided at no cost or obligation on the part of Soleno Textile Inc. The individual using this information in their possession assumes full responsibility for its use, including that of ensuring that this technical data sheet is the latest update by contacting Soleno Textile Inc. Values are calculated using the minimum average roll value (MARV), as defined by ASTM D-4439. Roll sizes can vary 0.5 % from standard sizes.

Soleno Textile Inc. offers no guarantee regarding the use, installation or suitability of the geotextiles described in this document. Since conditions surrounding the use and handling of our products can vary and are beyond the control of Soleno Textile Inc., it can in no way be held responsible for the product's performance and the consequences of improper installation or use. Soleno Textile Inc. must be advised of any defect or non-compliance of its product before installation. Soleno Textile Inc.'s liability will be limited to the replacement of the deficient or defective product to the exclusion of any legal or contractual warranty.

**APPLICATIONS:** Temporary roadway Permanent public roadway Permanent private roadway Public access road Commercial parking areas

Storage and loading areas Roadway widening Airport runways Railway tracks