

DATA SHEET

TX-400

PRODUCT DESCRIPTION : Nonwoven needled geotextile

FUNCTIONS : Separation, reinforcement and protection

PRODUCT SPECIFICATION : Meets Table 601-1 of the New Brunswick specification, N4

RAW MATERIAL : Polypropylene / polyester

TECHNICAL DATA TABLE

	PROPERTIES	TEST METHOD	VALUES	
			Metric	Imperial
PHYSICAL	Thickness	ASTM D5199	≥ 2.8 mm	≥ 112 mils
	Mass per unit area	ASTM D5261	-	-
MECHANICAL	Tensile strength	ASTM D4632	≥ 1200 N	≥ 270 lb
	Elongation at break	ASTM D4632	≥ 50 %	
	Tear strength	ASTM D4533	≥ 530 N	≥ 119 lb
	Puncture strength (CBR)	ASTM D6241	≥ 3450 N	≥ 776 lb
HYDRAULIC	Flow rate	ASTM D4491	≥ 0.19 cm/s	
	Permittivity	ASTM D4491	≥ 1.00 s ⁻¹	
	Apparent opening size (AOS) ⁽¹⁾	ASTM D4751	150 µm	100 US Sieve
	Filtration opening size (FOS)	CAN/CGSB-148,1 - No 10	50 - 90 µm	
PERFORMANCE AND DURABILITY	UV* resistance (500 hours)	ASTM D4355	≥ 70 %	
DIMENSIONS	Standard width	-	3.81 m	12.5 ft
	Standard length	-	100 m	328 ft

NOTE 1 : Maximum test value
*UV: Ultraviolet.

The information contained herein is provided at no cost or obligation on the part of Soleno Textile Inc. The individual using this information in their possession assumes full responsibility for its use, including that of ensuring that this technical data sheet is the latest update by contacting Soleno Textile Inc. Values are calculated using the minimum average roll value (MARV), as defined by ASTM D-4439. Roll sizes can vary 0.5% from standard sizes. Puncture strength (ASTM D4833) is no longer recognized by AASHTO M288 and has been replaced by CBR puncture (ASTM D6241). Mullen Burst (ASTM D3786) have been removed by AASHTO M288. Soleno Textile Inc.'s quality control laboratory is certified by the Geosynthetic Accreditation Institute - Laboratory Accreditation Program (GAI-LAP).

Soleno Textile Inc. offers no guarantee regarding the use, installation or fitness for purpose of its geotextiles described in this document. Since conditions of use and handling of our products can vary and are beyond the control of Soleno Textile Inc., it can in no way be held responsible for the product's performance and the consequences of improper installation or use. Soleno Textile Inc. must be advised of any defect or non-compliance of its product before installation. Soleno Textile Inc.'s liability is limited to the replacement of the defective or noncompliant product, with the exception of any legal or contractual warranty.

APPLICATIONS : Railway tracks
Basins
Retaining walls and embankments
Bank protection
Dams and dikes

